

ACRYLITE[®] Resist ZK6SR polymer

Product Profile:

ACRYLITE[®] Resist ZK6SR polymer is an amorphous, impact-modified thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE[®] Resist acrylic polymers are:

- high weather resistance
- high light transmission
- improved resistance to stress cracking
- good melt flow rate
- easy to color

The special properties of ACRYLITE[®] Resist ZK6SR polymer are:

- high impact/break resistance and strength
- high melt strength for extrusion
- low melt flow rate
- medium heat resistance
- AMECA listed as ZK6 (x)

Application:

Used for extruded sheet, co-extruded sheet and extruded profiles.

Examples:

Cap stock, light covers, signs, fountain pens, appliance housings, appliance lenses and housewares.

Processing:

ACRYLITE[®] Resist ZK6SR polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® Resist ZK6SR polymer
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	6000 [41]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.23 [1.6]
Tensile Elongation @ Yield		%	D 638	5
Tensile Elongation @ Break		%	D 638	60
Flexural Strength		psi [MPa]	D 790	8000 [55.2]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.2 [1.4]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	1.1 [59]
Notched Izod	½" bar @23°C	ft-lb/in [J/m]	D 256	1.1 [59]
Notched Izod	¼" bar @0°C	ft-lb/in [J/m]	D 256	0.8 [43]
Rockwell Hardness		M Scale	D 785	40
Thermal Properties				
Vicat Softening Point	264 psi	°F [°C]	D 1525	196 [91]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	181 [83]
Coeff. of Linear Therm. Expansion	32 – 312°F	in/ in/°F	D 696	0.00005
Coeff. of Linear Therm. Expansion	0 – 100°C	mm/mm/°C	D 696	0.00009
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	1.3
Optical Properties				d = 3.2 mm
Light Transmission		%	D 1003	>90
Haze		%	D 1003	<2
Yellowness Index			D 1925	0.2
Other Properties				
Specific Gravity			D 792	1.16
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.004 – 0.007
Bulk Density		g/cc	D 1895	0.71

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Evonik Cyro LLC. Evonik's Business Unit Performance Polymers is a worldwide manufacturer of PMMA molding compounds sold under the trademark ACRYLITE® in the Americas and under the PLEXIGLAS® trademark everywhere outside of the Americas. ® = registered trademark

Evonik Cyro LLC 379 Interpace Parkway, Parsippany, NJ 07054 USA
 Phone: 800-631-5384 Email: cyro.polymer@evonik.com www.acrylite-polymers.com
 Technical Support: visit the TechKnowledge Center at cyro.custhelp.com

Ref. No.: 3526-1008-ACCESSDB R13606-A Date: 07/05/2011