

## Product Information

Page 1 of 2

### ACRYLITE PLUS® ZK4HR impact acrylic polymer

#### Product Profile:

ACRYLITE PLUS® ZK4HR impact acrylic polymer is an amorphous, impact-modified thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE PLUS® impact acrylic polymers are:

- high weather resistance
- high light transmission
- improved resistance to stress cracking
- good melt flow rate
- easy to color

The special properties of ACRYLITE PLUS ZK4HR polymer are:

- good impact/break resistance and strength
- medium melt flow rate
- high heat resistance

#### Application:

Used for injection molded parts.

#### Examples:

Luminaries, appliance housings, appliance lenses and housewares.

#### Processing:

ACRYLITE PLUS ZK4HR polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

#### Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

**Properties:**

	Parameter	Unit	ASTM-Standard	ACRYLITE PLUS® ZK4HR polymer
<b>Mechanical Properties</b>				Typical Value
Tensile Strength		psi [MPa]	D 638	11200 [77.2]
Tensile Modulus		x10 <sup>6</sup> psi [GPa]	D 638	0.32 [2.2]
Tensile Elongation @ Yield		%	D 638	5
Tensile Elongation @ Break		%	D 638	4 – 8
Flexural Strength		psi [MPa]	D 790	14500 [99.9]
Flexural Modulus		x10 <sup>6</sup> psi [GPa]	D 790	0.32 [2.2]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.45 [23.4]
Notched Izod	¼" bar @0°C	ft-lb/in [J/m]	D 256	0.45 [23.4]
Rockwell Hardness		M Scale	D 785	89
<b>Thermal Properties</b>				
Vicat Softening Point		°F [°C]	D 1525	214 [101]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	198 [92]
Coeff. of Linear Therm. Expansion	32 – 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 – 100°C	mm/mm/°C	D 696	0.000072
<b>Rheological Properties</b>				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	3.1
<b>Optical Properties</b>				d = 3.2 mm
Light Transmission		%	D 1003	>90
Haze		%	D 1003	<2
Yellowness Index			D 1925	0.3
<b>Other Properties</b>				
Specific Gravity			D 792	1.17
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.004 – 0.007
Bulk Density		g/cc	D 1895	0.71
<b>Recommended processing conditions</b>				
Predrying Temperature		°F [°C]		180 [82]
Predrying Time		hour		3 – 4
Melt Temperature		°F [°C]		450 – 480 [232 – 250]
Cylinder Temperature		°F [°C]		450 – 480 [232 – 250]
Mold Temperature		°F [°C]		110 – 180 [49 – 82]

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all technical and other advice are based on Evonik Cyro's present knowledge and experience. However, Evonik Cyro assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik Cyro reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK CYRO DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. ACRYLITE, ACRYLITE PLUS, ACRYMID, CYROLITE, CYREX, CYRO, CYROVU, Vu-Stat and XT polymer are registered trademarks of Evonik Cyro LLC. Evonik's Business Unit Performance Polymers is a worldwide manufacturer of PMMA molding compounds sold under the trademark ACRYLITE® in the Americas and under the PLEXIGLAS® trademark everywhere outside of the Americas. ® = registered trademark

Evonik Cyro LLC 379 Interpace Parkway, Parsippany, NJ 07054 USA  
 Phone: 800-631-5384 Email: cyro.polymer@evonik.com www.cyro.com  
 Technical Support: visit the TechKnowlogy Center at cyro.custhelp.com

