

Product Information

Page 1 of 2

CYREX® 200–8000 acrylic–polycarbonate alloy

Product Profile:

CYREX 200–8000 alloy is an opaque, acrylic–polycarbonate alloy with an impact strength that is higher than polycarbonate.

Typical properties of CYREX® acrylic–polycarbonate alloys are:

- outstanding impact strength and toughness
- excellent processing characteristics
- very good chemical resistance
- good heat resistance

The special property of CYREX 200–8000 alloy is:

- medium melt flow rate

Application:

Used for injection molding and extrusion of both thin and thick wall applications which require excellent toughness.

Examples:

Portable phone housings, pager housings, appliances, toys, furniture, automotive components, protective casings, extruded and thermoformed sheet.

Processing:

CYREX 200–8000 alloy can be processed in injection molding machines and extrusion lines with 3– zone general purpose screws.

Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	ASTM-Standard	CYREX® 200-8000 alloy
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	8850 [61.0]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.35 [2.4]
Tensile Elongation @ Yield		%	D 638	4.7
Tensile Elongation @ Break		%	D 638	58
Flexural Strength		psi [MPa]	D 790	12500 [86.2]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.35 [2.4]
Notched Izod	½" bar @23°C	ft-lb/in [J/m]	D 256	30.0 [1600]
Notched Izod	½" bar @0°C	ft-lb/in [J/m]	D 256	4.0 [213]
Rockwell Hardness		M Scale	D 785	46
Thermal Properties				
Vicat Softening Point		°F [°C]	D 1525	277 [136]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	214 [101]
Coeff. of Linear Therm. Expansion	32 – 312°F	in/ in/°F	D 696	0.000052
Coeff. of Linear Therm. Expansion	0 – 100°C	mm/mm/°C	D 696	0.0000936
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	3.9
Optical Properties				d = 3.2 mm
Light Transmission		%	D 1003	Opaque
Other Properties				
Specific Gravity			D 792	1.15
Water Absorption		% Max	D 570	0.26
Mold Shrinkage		in/in, mm/mm	D 955	0.004 – 0.008
Bulk Density		g/cc	D 1895	0.65
Recommended processing conditions				
Predrying Temperature		°F [°C]		180 [82]
Predrying Time		hour		3 – 4
Melt Temperature		°F [°C]		460 – 510 [238 – 265]
Cylinder Temperature		°F [°C]		390 – 510 [199 – 265]
Mold Temperature		°F [°C]		150 – 210 [65 – 99]

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all technical and other advice are based on Evonik Cyro's present knowledge and experience. However, Evonik Cyro assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik Cyro reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK CYRO DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. ACRYLITE, ACRYLITE PLUS, ACRYMID, CYROLITE, CYREX, CYRO, CYROVU, Vu-Stat and XT polymer are registered trademarks of Evonik Cyro LLC. Evonik's Business Unit Performance Polymers is a worldwide manufacturer of PMMA molding compounds sold under the trademark ACRYLITE® in the Americas and under the PLEXIGLAS® trademark everywhere outside of the Americas. ® = registered trademark

Evonik Cyro LLC 379 Interpace Parkway, Parsippany, NJ 07054 USA
 Phone: 800-631-5384 Email: cyro.polymer@evonik.com www.cyro.com
 Technical Support: visit the TechKnowlogy Center at cyro.custhelp.com

Evonik Röhm GmbH Kirschenallee D-64293 Darmstadt
 Phone: +49 6151 18-4772 Email: plexiglas.polymers@evonik.com www.plexiglas.net

Ref. No.: 3534-1008-ACCESSDB v0160-A Date: 11/07/2008

