

## ACRYLITE<sup>®</sup> H15 polymer

---

### Product Profile:

ACRYLITE<sup>®</sup> H15 acrylic polymer is an amorphous thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE<sup>®</sup> acrylic polymers are:

- excellent weather resistance
- high light transmission
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE H15 polymer are:

- medium heat resistance
- high melt strength
- UV light absorption options
- lubricant options
- AMECA listed

### Application:

Used for injection molding and extrusion of optical and technical parts.

### Examples:

Extruded rods, tubes and profiles, light guides, pipes, medical and electronic instrument lenses, automotive rear light lenses, automotive cluster lenses, medical analysis devices and point-of-purchase displays.

### Processing:

ACRYLITE H15 polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

### Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

## Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® H15 polymer
<b>Mechanical Properties</b>				Typical Value
Tensile Strength		psi [MPa]	D 638	9800 [67.6]
Tensile Modulus		x10 <sup>6</sup> psi [GPa]	D 638	0.47 [3.2]
Tensile Elongation @ Yield		%	D 638	4 – 6
Tensile Elongation @ Break		%	D 638	4 – 6
Flexural Strength		psi [MPa]	D 790	17000 [117.2]
Flexural Modulus		x10 <sup>6</sup> psi [GPa]	D 790	0.49 [3.4]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.36 [19]
Rockwell Hardness		M Scale	D 785	95
<b>Thermal Properties</b>				
Vicat Softening Point	264 psi	°F [°C]	D 1525	221 [105]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	203 [96]
Coeff. of Linear Therm. Expansion	32 – 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 – 100°C	mm/mm/°C	D 696	0.000072
<b>Rheological Properties</b>				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	2.2
<b>Optical Properties</b>				
	d = 3.2 mm			
Light Transmission		%	D 1003	92
Haze		%	D 1003	<1
Yellowness Index			D 1925	<1
<b>Other Properties</b>				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.004 – 0.007
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Evonik Cyro LLC. Evonik's Business Unit Performance Polymers is a worldwide manufacturer of PMMA molding compounds sold under the trademark ACRYLITE® in the Americas and under the PLEXIGLAS® trademark everywhere outside of the Americas. ® = registered trademark

Evonik Cyro LLC 379 Interpace Parkway, Parsippany, NJ 07054 USA  
 Phone: 800-631-5384 Email: cyro.polymer@evonik.com www.acrylite-polymers.com  
 Technical Support: visit the TechKnowledge Center at cyro.custhelp.com

Ref. No.: 3542-1008-ACCESSDB R13606-A Date: 07/05/2011