

## ACRYLITE® H15 polymer

### Product Profile:

ACRYLITE® H15 acrylic polymer is an amorphous thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE® acrylic polymers are:

- excellent weather resistance
- high light transmission
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE H15 polymer are:

- medium heat resistance
- high melt strength
- UV light absorption options
- lubricant options
- AMECA listed

### Application:

Used for injection molding and extrusion of optical and technical parts.

### Examples:

Extruded rods, tubes and profiles, light guides, pipes, medical and electronic instrument lenses, automotive rear light lenses, automotive cluster lenses, medical analysis devices and point-of-purchase displays.

### Processing:

ACRYLITE H15 polymer can be processed in injection molding machines and extrusion lines with 3-zone general purpose screws.

### Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

## Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® H15 polymer
<b>Mechanical Properties</b>				Typical Value
Tensile Strength		psi [MPa]	D 638	9800 [67.6]
Tensile Modulus		x10 <sup>6</sup> psi [GPa]	D 638	0.47 [3.2]
Tensile Elongation @ Yield		%	D 638	4 - 6
Tensile Elongation @ Break		%	D 638	4 - 6
Flexural Strength		psi [MPa]	D 790	17000 [117.2]
Flexural Modulus		x10 <sup>6</sup> psi [GPa]	D 790	0.49 [3.4]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.36 [19]
Rockwell Hardness		M Scale	D 785	95
<b>Thermal Properties</b>				
Vicat Softening Point	264 psi	°F [°C]	D 1525	221 [105]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	203 [96]
Coeff. of Linear Therm. Expansion	32 - 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	mm/mm/°C	D 696	0.000072
<b>Rheological Properties</b>				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	2.2
<b>Optical Properties</b>				d = 3.2 mm
Light Transmission		%	D 1003	92
Haze		%	D 1003	<1
Yellowness Index			D 1925	<1
<b>Other Properties</b>				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.004 - 0.007
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054  
[www.acrylite-polymers.de](http://www.acrylite-polymers.de)  
[www.roehm.com](http://www.roehm.com)

Ref. No.: 3542-1008-ACCESSDB A1142-A Date: 02/04/2020