

## PRODUCT INFORMATION

# ACRYLITE® Heatresist hw55 acrylic polymer

### Product Profile:

ACRYLITE® Heatresist hw55 acrylic polymer is a copolymer based on methyl methacrylate (MMA) with comonomer constituents for injection molding applications.

Typical properties of ACRYLITE® Heatresist acrylic polymers are:

- excellent weather resistance
- high light transmission
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE® Heatresist hw55 polymer are:

- high heat resistance
- high melt strength
- improved resistance to isopropyl alcohol
- AMECA listed

### Application:

Used for injection molding of technical parts for applications subjected to high thermal stress.

### Examples:

Automotive rear light lenses, lighted keys, light covers, reflex lenses and fog light lenses.

### Processing:

ACRYLITE® Heatresist hw55 polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

ACRYLITE® Heatresist hw55 polymer exhibits heat sensitivity during processing therefore follow our recommended process

### Physical Form / Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

**Properties:**

	Parameter	Unit	ASTM-Standard	ACRYLITE® Heatresist hw55 acrylic polymer Typical Value
<b>Mechanical Properties</b>				
Tensile Strength		psi [MPa]	D 638	12500 [86]
Tensile Modulus		x10 <sup>6</sup> psi [GPa]	D 638	0.55 [3.8]
Tensile Elongation @ Yield		%	D 638	2 - 4
Tensile Elongation @ Break		%	D 638	2 - 4
Flexural Strength		psi [MPa]	D 790	19800 [136.5]
Flexural Modulus		x10 <sup>6</sup> psi [GPa]	D 790	0.50 [3.5]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.25 [13]
Rockwell Hardness		M Scale	D 785	100
<b>Thermal Properties</b>				
Vicat Softening Point	50N, 50°C/h	°F [°C]	D 1525	246 [119]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	223 [106]
Coeff. of Linear Therm. Expansion	32 - 312°F	1/F	D 696	0.000056
<b>Rheological Properties</b>				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	1.3
<b>Optical Properties</b>				d = 3.2 mm
Light Transmission		%	D 1003	91
Haze		%	D 1003	<1
<b>Other Properties</b>				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.009-0.010

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Roehm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved

Roehm America LLC • 8 Campus Drive • Parsippany NJ 07054 • USA  
[www.acrylite-polymers.com](http://www.acrylite-polymers.com)  
[www.roehm.com](http://www.roehm.com)

Ref. No.: MC145 A1142

