

ACRYLITE® Hi-Gloss FT-8 polymer

Product Profile:

ACRYLITE® Hi-Gloss FT-8 polymer is an amorphous thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

ACRYLITE® Hi-Gloss FT-8 polymer is available in a range of opaque colors including deep jet black.

Typical properties of ACRYLITE® Hi-Gloss acrylic polymers are:

- excellent weather resistance
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE® Hi-Gloss FT-8 polymer are:

- high heat resistance
- high melt strength
- available in a range of opaque colors

Application:

Used for injection molding of automotive parts.

Examples:

Automotive surface parts (e.g. exterior pillars, mirror housings and exterior covers); Can be used to replace Class A painted applications.

Processing:

ACRYLITE® Hi-Gloss FT-8 polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	Standard	ACRYLITE® Hi-Gloss FT-8 polymer
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3300
Stress @ Break	5 mm/min	MPa	ISO 527	77
Strain @ Break	5 mm/min	%	ISO 527	5.5
Charpy Impact Strength	23°C	kJ/m²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	108
Glass Transition Temperature		°C	ISO 11357	117
Deflection Temperature Under Load	0.45 MPa	°C	ISO 75	103
Deflection Temperature Under Load	1.8 MPa	°C	ISO 75	98
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	8
Classes of construction product			DIN EN 13501-1	E
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm³/10min	ISO 1133	3
Other Properties				
Density		g/cm³	ISO 1183	1.19

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054
www.acrylite-polymers.de
www.roehm.com

Ref. No.: 3360A-1008-ACCESSDB A1142-I Date: 02/04/2020