

ACRYLITE® Hi-Gloss FT15 polymer

Product Profile:

ACRYLITE® Hi-Gloss FT15 polymer is an amorphous thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

ACRYLITE® Hi-Gloss FT15 polymer is available in a range of opaque colors including deep jet black.

Typical properties of ACRYLITE® Hi-Gloss acrylic polymers are:

- excellent weather resistance
- high light transmission
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE® Hi-Gloss FT15 polymer are:

- high heat resistance
- available in transparent and a range of opaque colors
- medium melt flow rate
- AMECA listed

Application:

Used for injection molding and extrusion applications.

Examples:

Automotive surface parts (e.g. exterior appliquéés); automotive lights, and luminaire covers for high heat lighting applications (exterior and interior).

Processing:

ACRYLITE® Hi-Gloss FT15 polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	Standard	ACRYLITE® Hi-Gloss FT15 polymer
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3500
Stress @ Break	5 mm/min	MPa	ISO 527	50
Strain @ Break	5 mm/min	%	ISO 527	3.1
Charpy Impact Strength	23°C	kJ/m²	ISO 179/1eU	18
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	115
Glass Transition Temperature		°C	ISO 11357	121
Deflection Temperature Under Load	0.45 MPa	°C	ISO 75	107
Deflection Temperature Under Load	1.8 MPa	°C	ISO 75	105
Classes of construction product			DIN EN 13501-1	E
Glow Wire Ignition Temperature		°C	IEC 60695-2	675
Rheological Properties				
Melt Volume Rate, MVR	230°C & 3.8kg	cm³/10min	ISO 1133	4.5
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	Opaque
Refractive Index			ISO 489	Opaque
Other Properties				
Density		g/cm³	ISO 1183	1.19

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054
www.acrylite-polymers.de
www.roehm.com

Ref. No.: A1142-I Date: 02/04/2020