

## ACRYLITE® Hi-Gloss NTA-1 polymer

### Product Profile:

ACRYLITE® Hi-Gloss NTA-1 polymer is an opaque, amorphous, and impact-modified thermoplastic molding and extrusion compound based on polymethyl methacrylate.

Typical properties of ACRYLITE® Hi-Gloss acrylic polymers are:

- excellent weather resistance
- improved resistance to stress cracking
- good melt flow rate
- good polishability
- impact resistance

The special properties of ACRYLITE® Hi-Gloss NTA-1 polymer are:

- good heat resistance
- available in a range of opaque colors
- high melt strength
- increased impact/break resistance and strength

### Application:

Used for injection molding technical parts.

### Examples:

Automotive surface parts such as exterior pillars, mirror housings, pillar panels, spoiler, two-shot structural protection applications where acrylic is applied over other non-weatherable polymers, emblems and interior trim; housings for consumer products.

### Processing:

ACRYLITE® Hi-Gloss NTA-1 polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

### Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

## Properties:

	Parameter	Unit	Standard	ACRYLITE® Hi-Gloss NTA-1 polymer
<b>Mechanical Properties</b>				
Tensile Modulus	1 mm/min	MPa	ISO 527	2700
Yield Stress	50 mm/min	MPa	ISO 527	68
Yield Strain	50 mm/min	%	ISO 527	5
Nominal Strain @ Break		%	ISO 527	10
Charpy Impact Strength	23°C	kJ/m <sup>2</sup>	ISO 179/1eU	33
<b>Thermal Properties</b>				
Vicat Softening Temperature	B / 50	°C	ISO 306	110
Glass Transition Temperature		°C	ISO 11357	120
Deflection Temperature Under Load	0.45 MPa	°C	ISO 75	103
Deflection Temperature Under Load	1.8 MPa	°C	ISO 75	102
Classes of construction product			DIN EN 13501-1	E
Glow Wire Ignition Temperature		°C	IEC 60695-2	675
<b>Rheological Properties</b>				
Melt Volume Rate, MVR	230°C & 3.8kg	cm <sup>3</sup> /10min	ISO 1133	3
<b>Other Properties</b>				
Density		g/cm <sup>3</sup>	ISO 1183	1.18
Water Absorption		% max.	ISO 62	> 3

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054  
[www.acrylite-polymers.de](http://www.acrylite-polymers.de)  
[www.roehm.com](http://www.roehm.com)

Ref. No.: 3362A-1008-ACCESSDB A1142-I Date: 02/04/2020