

PRODUCT INFORMATION

ACRYLITE® Hi-Gloss NTA-5 black 9V022

Product Profile:

ACRYLITE® Hi-Gloss NTA-5 black 9V022 is an amorphous thermoplastic molding compound, based on impact-modified polymethyl methacrylate (PMMA).

ACRYLITE® molding compounds have the following typical properties:

- high weather resistance
- brilliant appearance
- 100 % recyclable

ACRYLITE® Hi-Gloss NTA-5 black 9V022 is characterized by the following additional properties:

- highest breaking strength and impact resistance
- increased heat resistance
- improved resistance to stress cracking
- balanced property profile

Application:

ACRYLITE® Hi-Gloss NTA-5 black 9V022 is particularly suitable for injection molding of technical components where high impact resistance is needed. Due to its superior brilliance high-gloss Class A surfaces can be obtained without painting.

Examples:

Add-on automotive body parts, pillar-trims, mirror housings, trim parts at front – and rear end, etc.

Processing:

ACRYLITE® Hi-Gloss NTA-5 black 9V022 can be processed by injection molding with a three-section screw suitable for the processing of PMMA.

Physical Form / Packaging:

ACRYLITE® Hi-Gloss NTA-5 black 9V022 are supplied as cylindrical pellets in 25 kg polyethylene bags or 500 kg boxes with PE lining.

Properties:

	Parameter	Unit	Standard	ACRYLITE® Hi-Gloss NTA-5 black 9V022
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	2100
Yield Stress	50 mm/min	MPa	ISO 527	54
Yield Strain	50 mm/min	%	ISO 527	5
Nominal Strain @ Break		%	ISO 527	48
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	110
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	103
Glass Transition Temperature		°C	ISO 11357	113
Temp. of Deflection under Load	0.45 MPa	°C	ISO 75	102
Temp. of Deflection under Load	1.8 MPa	°C	ISO 75	96
Coeff. of Linear Therm. Expansion	0 - 50°C	E-5 /°K	ISO 11359	11
Flammability UL 94	1.5 mm	Class	IEC 60695-11-10	HB
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3,8kg	cm ³ /10min	ISO 1133	1,3
Optical Properties				
	d=3 mm			
Other Properties				
Density		g/cm ³	ISO 1183	1.16
Water Absorption in Water	saturation, 23°C	%	ISO 62	1,5
Humidity Absorption	23°C / 50%	%	ISO 62	0,5
Recommended Processing Conditions				
Predrying Temperature		°C		80
Predrying Time in Desiccant-Type Drier		h		> 4
Melt Temperature		°C		230 - 260
Mold Temperature (Injection Molding)		°C		60 - 80

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

Röhm is a worldwide manufacturer of PMMA products sold under the PLEXIGLAS® trademark on the European, Asian, African and Australian continents and under the ACRYLITE® trademark in the Americas.

® = registered trademark

PLEXIGLAS and PLEXIMID are registered trademarks of Röhm GmbH.

Röhm GmbH • Darmstadt • Germany
plexiglas.polymers@roehm.com
www.plexiglas-polymers.com

Ref. No.: MC296 A1142

RÖHM