

PRODUCT INFORMATION

ACRYLITE® L40 acrylic polymer

Product Profile:

ACRYLITE® L40 acrylic polymer is an amorphous thermoplastic molding compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE® acrylic polymers are:

- excellent weather resistance
- high light transmission
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- versatile colorability due to crystal clarity

The special properties of ACRYLITE® L40 polymer are:

- low heat resistance
- highest melt flow rate
- UV light transmitting
- medium levels of lubricant

Application:

Used for injection molding thin-wall medical devices requiring UV spectroscopy for fluid evaluation.

Examples:

Medical diagnostic parts including cuvettes, test packs and rotors.

Processing:

ACRYLITE® L40 polymer can be processed in injection molding machines with 3- zone general purpose screws.

Physical Form / Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® L40 acrylic polymer Typical Value
Mechanical Properties				
Tensile Strength		psi [MPa]	D 638	8800 [60.7]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.47 [3.2]
Tensile Elongation @ Yield		%	D 638	2 - 4
Tensile Elongation @ Break		%	D 638	2 - 4
Flexural Strength		psi [MPa]	D 790	14200 [97.9]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.44 [3.0]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.36 [19]
Rockwell Hardness		M Scale	D 785	84
Thermal Properties				
Vicat Softening Point	50N, 50°C/h	°F [°C]	D 1525	180 [82]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	165 [74]
Coeff. of Linear Therm. Expansion	32 - 312°F	1/F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	1/C	D 696	0.000072
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	26.0
Optical Properties				
	d = 3.2 mm			
Light Transmission		%	D 1003	92
Haze		%	D 1003	<1
Yellowness Index			E 313	<1
Other Properties				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.003 - 0.006
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer.

Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Roehm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved

Roehm America LLC • 8 Campus Drive • Parsippany NJ 07054 • USA
www.acrylite-polymers.com
www.roehm.com

Ref. No.: MC154 A1142

The logo for RÖHM, featuring the word "RÖHM" in a bold, black, sans-serif font. The letter "O" is stylized with a small circle above it, resembling a dot or a specific character.