

ACRYLITE® LED 8N LD96

Product Profile:

ACRYLITE® LED 8N LD96 Acrylic Molding Compound is a highly transparent light guide material based on ACRYLITE® 8N.

In addition to the typical properties of ACRYLITE®, such as

- Excellent weather resistance
- UV-stability
- Good flow, high mechanical strength

ACRYLITE® LED 8N LD96 is developed for edge lit LED applications. The light scattering properties convert the light guide to a full illuminated panel. Furthermore, the material allows for a completely transparent view through the light guide when it is not illuminated. This opens a new degree of freedom for designers. ACRYLITE® 8N LD12 is recommended for panels with a distance of 48 cm to 96 cm between two light injecting LED strips.

Application:

Injection molding or extrusion.

Examples:

BLU (Back lighting) for LCD-Displays, illuminated freeform panels, ambient lighting, illuminated handle bars and switches. Illuminated outline contours for devices.

Processing:

ACRYLITE® LED 8N LD96 can be processed on injection molding machines with 3-zone general purpose screws for engineering thermoplastics.

Packaging:

ACRYLITE® LED 8N LD molding compounds are supplied as pellets of uniform size, packaged in 1500 pound gaylords; other packaging on request.

Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® LED 8N LD96
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	11300 [77.9]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.47 [3.2]
Tensile Elongation @ Yield		%	D 638	4 - 6
Tensile Elongation @ Break		%	D 638	4 - 6
Flexural Strength		psi [MPa]	D 790	16200 [111.7]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.5 [3.5]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.36 [19]
Rockwell Hardness		M Scale	D 785	95
Thermal Properties				
Vicat Softening Point	264 psi	°F [°C]	D 1525	226[108]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	212 [100]
Coeff. of Linear Therm. Expansion	32 - 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	mm/mm/°C	D 696	0.000072
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	3.3
Optical Properties				d = 3.2 mm
Light Transmission		%	D 1003	92
Haze		%	D 1003	<1
Yellowness Index			D 1925	<1
Other Properties				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.004 - 0.007
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054
www.acrylite-polymers.de
www.roehm.com

Ref. No.: A1142-A Date: 02/04/2020