

PRODUCT INFORMATION

ACRYLITE® Softlight 8N df20

Product Profile:

ACRYLITE® Softlight 8N df20, based on ACRYLITE® 8N, is characterized by diffuse scattering of light.

Besides showing the familiar properties of standard ACRYLITE® molding compound, such as

- excellent weatherability,
- high surface hardness and mar resistance,
- UL registration RTI90 by (fi) 746C.

ACRYLITE® Softlight 8N df20 is special in that they combine

- good diffusing power with excellent light transmission.

Application:

Used for injection molding items for lighting engineering applications

Examples:

displays, fiber optics, projection screens, lighting fixtures and similar applications in lighting engineering.

Processing:

ACRYLITE® Softlight 8N df20 can be processed on injection molding machines with 3-zone general purpose screws for thermoplastics.

Physical Form / Packaging:

ACRYLITE® Softlight df molding compounds are supplied as pellets of uniform size, packaged in 25kg polyethylene bags; other packaging on request.

Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® Softlight 8N df20 Typical Value
Mechanical Properties				
Tensile Strength		psi [MPa]	D 638	11350 [78.3]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.54 [3.7]
Tensile Elongation @ Yield		%	D 638	4
Tensile Elongation @ Break		%	D 638	4
Flexural Strength		psi [MPa]	D 790	19000 [131]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.5 [3.5]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.3 [16]
Rockwell Hardness		M Scale	D 785	95
Thermal Properties				
Vicat Softening Point	50N, 50°C/h	°F [°C]	D 1525	226[108]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	221 [105]
Coeff. of Linear Therm. Expansion	32 - 312°F	1/F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 - 100°C	1/C	D 696	0.000072
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	3.2
Optical Properties				
	d = 3.2 mm			
Light Transmission		%	D 1003	90
Haze		%	D 1003	50
Yellowness Index			E 313	<1
Other Properties				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.003 - 0.006
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

Certified to ISO 9001:2015, ISO 14001:2015 and IATF 16949:2016.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer.

Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Roehm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved

Roehm America LLC • 8 Campus Drive • Parsippany NJ 07054 • USA
www.acrylite-polymers.com
www.roehm.com

Ref. No.: MC600 A1142

The logo for RÖHM, featuring the word "RÖHM" in a bold, black, sans-serif font. The letter "O" is stylized with a small circle above it, resembling a dot or a specific character.