

ACRYLITE® Resist ZK-D polymer

Product Profile:

ACRYLITE® Resist ZK-D polymer is an amorphous, impact-modified thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA).

Typical properties of ACRYLITE® Resist acrylic polymers are:

- high weather resistance
- high light transmission
- improved resistance to stress cracking
- good melt flow rate
- easy to color

The special properties of ACRYLITE® Resist ZK-D polymer are:

- High impact/break resistance and strength
- medium melt flow rate
- medium heat resistance

Application:

Used for injection molded parts, extruded and co-extruded sheet and profiles.

Examples:

Applications involving thin walls and long flow paths, parts requiring accurate mold surface reproduction, wind deflectors, point-of-purchase displays, light covers, fountain pens, appliance housings, appliance lenses and housewares.

Processing:

ACRYLITE® Resist ZK-D polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

Properties:

	Parameter	Unit	ASTM-Standard	ACRYLITE® Resist ZK-D polymer
Mechanical Properties				Typical Value
Tensile Strength		psi [MPa]	D 638	6400 [44.1]
Tensile Modulus		x10 ⁶ psi [GPa]	D 638	0.23 [1.6]
Tensile Elongation @ Yield		%	D 638	5
Tensile Elongation @ Break		%	D 638	40
Flexural Strength		psi [MPa]	D 790	9400 [64.8]
Flexural Modulus		x10 ⁶ psi [GPa]	D 790	0.23 [1.6]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	1.1 [58.1]
Notched Izod	¼" bar @0°C	ft-lb/in [J/m]	D 256	0.65 [34.1]
Rockwell Hardness		M Scale	D 785	33
Thermal Properties				
Vicat Softening Point	264 psi	°F [°C]	D 1525	201 [94]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	190 [88]
Coeff. of Linear Therm. Expansion	32 - 312°F	in/ in/°F	D 696	0.000052
Coeff. of Linear Therm. Expansion	0 - 100°C	mm/mm/°C	D 696	0.0000936
Rheological Properties				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	5.8
Optical Properties				d = 3.2 mm
Light Transmission		%	D 1003	91.5
Haze		%	D 1003	1
Yellowness Index			D 1925	0.3
Other Properties				
Specific Gravity			D 792	1.16
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.003 - 0.006
Bulk Density		g/cc	D 1895	0.71

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054
www.acrylite-polymers.de
www.roehm.com

Ref. No.: 3560-1008-ACCESSDB A1142-A Date: 02/04/2020