

## ACRYLITE<sup>®</sup> Satinice df 23 8N polymer

---

### Product Profile:

ACRYLITE<sup>®</sup> Satinice df 23 8N polymer is an amorphous thermoplastic molding and extrusion compound based on polymethyl methacrylate (PMMA) and diffusion polymers.

Typical properties of ACRYLITE<sup>®</sup> Satinice acrylic polymers are:

- excellent weather resistance
- high mechanical strength
- high surface hardness and mar resistance
- good melt flow rate
- superior light diffusion (hiding power) and transmittance

The special properties of ACRYLITE<sup>®</sup> Satinice df 23 8N polymer are:

- excellent light diffusion combined with excellent light transmission
- highest heat resistance
- high melt strength
- low levels of lubricant

### Application:

Used for injection molding and extrusion of lighting luminaries, instrument displays and extruded profiles.

### Examples:

Commercial and residential lighting covers, electronics and point-of-purchase displays.

### Processing:

ACRYLITE<sup>®</sup> Satinice df 23 8N polymer can be processed in injection molding machines and extrusion lines with 3- zone general purpose screws.

### Packaging:

Available in 1500 lb. gaylord boxes; other packaging available on request.

**Properties:**

	Parameter	Unit	ASTM-Standard	ACRYLITE® Satinice df 23 8N polymer
<b>Mechanical Properties</b>				Typical Value
Tensile Strength		psi [MPa]	D 638	11 500 [79.3]
Tensile Modulus		x10 <sup>6</sup> psi [GPa]	D 638	0.55 [3.8]
Tensile Elongation @ Yield		%	D 638	4
Tensile Elongation @ Break		%	D 638	4
Flexural Strength		psi [MPa]	D 790	19000 [131]
Flexural Modulus		x10 <sup>6</sup> psi [GPa]	D 790	0.5 [3.5]
Notched Izod	¼" bar @23°C	ft-lb/in [J/m]	D 256	0.3 [16]
Rockwell Hardness		M Scale	D 785	95
<b>Thermal Properties</b>				
Vicat Softening Point	264 psi	°F [°C]	D 1525	246 [119]
Deflection Temperature, Annealed	1.8MPa, 0.250"	°F [°C]	D 648	221 [105]
Coeff. of Linear Therm. Expansion	32 – 312°F	in/ in/°F	D 696	0.00004
Coeff. of Linear Therm. Expansion	0 – 100°C	mm/mm/°C	D 696	0.000072
<b>Rheological Properties</b>				
Melt Flow Rate	230°C & 3.8 kg	g/10min	D 1238	2.9
<b>Optical Properties</b>				d = 3.2 mm
Light Transmission		%	D 1003	86
Haze		%	D 1003	96
Yellowness Index			D 1925	<6.5
<b>Other Properties</b>				
Specific Gravity			D 792	1.19
Water Absorption		% Max	D 570	0.3
Mold Shrinkage		in/in, mm/mm	D 955	0.003 – 0.006
Bulk Density		g/cc	D 1895	0.66

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all technical and other advice are based on Evonik's present knowledge and experience. However, Evonik assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Evonik Cyro LLC. Evonik's Business Unit Performance Polymers is a worldwide manufacturer of PMMA molding compounds sold under the trademark ACRYLITE® in the Americas and under the PLEXIGLAS® trademark everywhere outside of the Americas. ® = registered trademark

Evonik Cyro LLC 379 Interpace Parkway, Parsippany, NJ 07054 USA  
 Phone: 800-631-5384 Email: cyro.polymer@evonik.com www.acrylite-polymers.com  
 Technical Support: visit the TechKnowledge Center at cyro.custhelp.com

Ref. No.: 3520-1008-ACCESSDB R13606-A Date: 07/05/2011