

ACRYMID® TT70

Product Profile:

ACRYMID® TT70 is a highly heat distortion-resistant poly(n-methyl methacrylimide) (PMMI).

Besides showing the properties common to all ACRYMID® molding compounds, such as

- excellent transmission and clarity,
- very high mechanical strength and rigidity,
- good weather resistance.

ACRYMID® TT70 has the following specific characteristics:

- high stability of the optical characteristics at long-lasting thermal load,
- highest heat deflection temperature under load.

Application:

ACRYMID® molding compound is particularly suitable for injection molding of items meant for applications that involve maximum thermal loads.

Examples:

automotive lighting, light guides, lenses, fiber optics, luminaire covers, sight glasses, cover lenses.

Processing:

ACRYMID® molding compound can be processed on injection molding machines with standard 3-zone general purpose screws for thermoplastics.

Note: After a partial removal, we strongly recommend resealing the container in order to prevent permeation of moisture.

Packaging:

ACRYMID® is supplied as pellets of uniform size in aluminum-laminated, 25kg polyethylene bags; other packaging on request.

Properties:

	Parameter	Unit	Standard	ACRYMID® TT70
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	4000
Stress @ Break	5 mm/min	MPa	ISO 527	80
Strain @ Break	5 mm/min	%	ISO 527	3
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	170
Deflection Temperature Under Load	0.45 MPa	°C	ISO 75	158
Deflection Temperature Under Load	1.8 MPa	°C	ISO 75	149
Classes of construction product			DIN EN 13501-1	E
Rheological Properties				
Melt Volume Rate, MVR	260°C / 10kg	cm ³ /10min	ISO 1133	1.7
Optical Properties				
	d = 1mm			
Luminous transmittance	D65	%	ISO 13468-2	91
Refractive Index			ISO 489	1.54
Other Properties				
Density		g/cm ³	ISO 1183	1.21
Water Absorption		% max.	ISO 62	6
Recommended Processing Conditions				
Predrying Temperature		°C		max. 120
Predrying Time in Desiccant-Type Drier		h		2 - 3
Melt Temperature		°C		260 - 290
Mold Temperature (Injection Molding)		°C		ca. 130

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all further technical advice is based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, Vu-Stat and XT polymer are registered trademarks of Roehm America LLC. Röhm is a worldwide manufacturer of PMMA products sold under the ACRYLITE® trademark in the Americas and under the PLEXIGLAS® trademark in the European, Asian, African and Australian continents. ©2017 Roehm America LLC. All rights reserved.

Roehm America LLC • 299 Jefferson Road • Parsippany NJ 07054
www.cyrolite.com
www.roehm.com

Ref. No.: A1142-I Date: 02/05/2020