

ACRYLITE® Solar IM20

Product Profile:

ACRYLITE® Solar IM20 is an amorphous thermoplastic molding compound (PMMA).

Typical properties of ACRYLITE® molding compounds are:

- Good flow
- High mechanical strength, surface hardness and abrasion resistance
- High light transmission
- Very good weather resistance
- Easy to process
- High heat resistance

Special properties of ACRYLITE® Solar IM20 are:

- Adjusted transmission characteristics for photo voltaic applications (PV, CPV)
- Increase of power yield and module efficiency
- Prolonging lifetime of cells, lenses or covers.

Application:

Field of use is injection molding of optical and technical parts as well as extrusion of profiles and sheets.

Examples:

Covers for build-in photo voltaic, radial and linear Fresnel lenses for CPV/CSP applications.

Processing:

ACRYLITE® Solar IM20 can be processed on injection molding and extrusion machines with 3-zone general purpose screws for engineering thermoplastics.

Packaging:

ACRYLITE® molding compounds are supplied as pellets of uniform size, packaged in 1500 pound gaylords; other packaging on request.

Properties:

	Parameter	Unit	Standard	ACRYLITE® Solar IM20
Mechanical Properties				
Tensile Modulus	1 mm/min	MPa	ISO 527	3300
Stress @ Break	5 mm/min	MPa	ISO 527	77
Strain @ Break	5 mm/min	%	ISO 527	5.5
Charpy Impact Strength	23°C	kJ/m ²	ISO 179/1eU	20
Thermal Properties				
Vicat Softening Temperature	B / 50	°C	ISO 306	108
Glass Transition Temperature		°C	IEC 10006	117
Deflection Temperature Under Load	0.45 MPa	°C	ISO 75	103
Deflection Temperature Under Load	1.8 MPa	°C	ISO 75	98
Coeff. of Linear Therm. Expansion	0 – 50°C	E-5 /°K	ISO 11359	8
Fire Rating			DIN 4102	B2
Rheological Properties				
Melt Volume Rate, MVR	230°C / 3.8kg	cm ³ /10min	ISO 1133	3
Optical Properties				
Luminous transmittance	d=3 mm			
Luminous transmittance	D65	%	ISO 13468-2	92
Haze		%	ASTM D1003	< 0.5
Refractive Index			ISO 489	1.49
Other Properties				
Density		g/cm ³	ISO 1183	1.19

All listed technical data are typical values intended for your guidance. They are given without obligation and do not constitute a materials specification.

This information and all technical and other advice are based on Evonik Cyro's present knowledge and experience. However, Evonik Cyro assumes no liability for such information or advice, including the extent to which such information or advice may relate to third party intellectual property rights. Evonik Cyro reserves the right to make any changes to information or advice at any time, without prior or subsequent notice. EVONIK CYRO DISCLAIMS ALL REPRESENTATIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, AND SHALL HAVE NO LIABILITY FOR, MERCHANTABILITY OF THE PRODUCT OR ITS FITNESS FOR A PARTICULAR PURPOSE (EVEN IF EVONIK IS AWARE OF SUCH PURPOSE), OR OTHERWISE. EVONIK SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. It is the customer's sole responsibility to arrange for inspection and testing of all products by qualified experts. Reference to trade names used by other companies is neither a recommendation nor an endorsement of the corresponding product, and does not imply that similar products could not be used. ACRYLITE, ACRYMID, CYROLITE, CYREX, CYRO, CYROVU, Vu-Stat and XT polymer are registered trademarks of Evonik Cyro LLC. Evonik's Business Unit Performance Polymers is a worldwide manufacturer of PMMA molding compounds sold under the trademark ACRYLITE® in the Americas and under the PLEXIGLAS® trademark everywhere outside of the Americas. ® = registered trademark

Evonik Cyro LLC 379 Interpace Parkway, Parsippany, NJ 07054 USA
Phone: 800-631-5384 Email: cyro.polymer@evonik.com www.cyro.com
Technical Support: visit the TechKnowledge Center at cyro.custhelp.com

Ref. No.: v0160-I Date: 03/31/2011